

DEKOMA®

matrix fr

matrix fr




Snow 81



Champagne 80



Cream 88



Vanilla 86



Nude 36




Mist 51




Grey 57




Dust 58



Red 20




Brown 46



Espresso 41



Black 10



Red 20

name	MATRIX FR		
composition	70% PVC, 16% PL, 12% CO, 2% PU		
composition surface	96% PVC, 4% PU		
composition backing	67% PL, 33% CO		
weight ±	650 g/m²		
usable width ±	140 cm		
thickness ±	EN ISO 2686-3	1,2 mm	
abrasion resistance Martindale cycles	EN ISO 12947-2	100 000	
tear strenght	EN ISO 4674	↑ 29	→ 28
elongation at break	EN ISO 1421	↑ 5	→ 12 %
colour fastness to rubbing (1-5)	EN ISO 105-X12	wet 4 dry 4	
flame retardant standards	EN 1021 BS 5852 US Cal. Bull. 117	1,2 0,1 (when using flammable foam 20-22 kg/m3) Passed	
type	upholstery decorative		
cleaning	<p>Clean regularly with warm water, neutral soap and a micro-fiber cloth or soft hand brush. Rinse with warm water, with a cotton cloth. Do not use solvents, chlorides, alcohol, abrasives, chemical cleaning agents or wax polishes.</p> <p>Staining by Jeans or other textiles are excluded from any manufacturer's guarantee. Wrinkles appearing on the surface are natural characteristics of a genuine leather. More detailed cleaning instructions available on our website.</p>		

legend

PVC - Vinyl Polichloride
PU - Polyurethane
PL - Polyester
CO - Cotton

Colour shades may slightly vary from dye-lot to dye-lot.
For more details, visit our website dekoma.eu



**flame
retardant**



upholstery



decorative

