

PRODUCT DATA SHEET



product name:**CAVO**

collection:**CAVO**

Basic information

	Result
width total (+/-)	145 cm
width usable (+/-)	143 cm
weight (+/-)	330 g/m²
roll length (+/- 5m)	45 m
minimal order quantity	0.1 m
quantity of colours	41

Composition

trevira cs	100%
------------	-------------

Technical data

	Norm	Result
abrasion resistance	EN ISO 12 947	61 000 Martindale cycles
colour resistance to light	EN ISO 105-B02	5-6
color fastness to wet rubbing	EN ISO 105-X12	3-4
color fastness to dry rubbing	EN ISO 105-X12	4-5

seam slippage	EN ISO 13 936-2	warp 1 mm weft 1 mm
pillling	EN ISO 12 945-2	4

Acoustic properties

Norm		Result
EN ISO 354 & 11654		0.75 CLASS C

Flame retardant standards

Norm	Foam	Result
EN 13773		Class 1
BS 5852	$\geq 30 \text{ kg/m}^3$	0
BS 5852	$\geq 30 \text{ kg/m}^3$	1
BS 5852	FR $\geq 50 \text{ kg/m}^3$	Crib 5
EN 1021	$\geq 30 \text{ kg/m}^3$	1
EN 1021	$\geq 30 \text{ kg/m}^3$	2
IMO	FR 36 kg/m^3	zdane
NF P 92-507		M1
BS 5867 PART 2		Type C
DIN 4102		B1

Applications / parameters

flame retardant



curtains



upholstery



decorative



oeko tex



imo



acoustic
properties



Maintenance



wash at maximum 30 °c



do not bleach



tolerates ironing up to 110 °c



normal dry cleaning using hydrocarbons and tetrachloroethene



do not tumble dry

Before you order

1. Colour shades may vary slightly between production lots.
2. Information presented on this website does not constitute a trade offer.
3. Product technical parameters contained in the safety data sheet are based on the manufacturer's data.
4. Data on maintenance (cleaning methods) pertains to the fabrics we sell, not to finished products comprising different elements.
5. Before cutting the fabric, please verify the quantity delivered, quality of materials and conformity with the order.
6. With complete rolls of textiles, the length may differ slightly from the value declared.
7. In case of any doubts regarding the use of our products, visit the TIPS section at www.dekoma.eu or contact us directly.
8. Colours of products presented on this website may differ from the actual colours.
9. Due to the specific character of the production process, the parameters provided i.e. width, height, grammage, and repeat may differ slightly from the values declared.