

## PRODUCT DATA SHEET



product name:**PEDRO**

collection:**PEDRO**

### Basic information

	Result
width total (+/-)	<b>140 cm</b>
width usable (+/-)	<b>140 cm</b>
report ↑	<b>0.7 cm</b>
report →	<b>0.5 cm</b>
weight (+/-)	<b>472 g/m<sup>2</sup></b>
roll length (+/- 5m)	<b>50 m</b>
minimal order quantity	<b>0.1 m</b>
quantity of colours	<b>6</b>

### Composition

polyester	<b>100%</b>
-----------	-------------

### Technical data

	Norm	Result
abrasion resistance	EN ISO 12 947-2	<b>70 000 Martindale cycles</b>
colour resistance to light	EN ISO 105-B02	<b>5-6</b>
color fastness to wet rubbing	EN ISO 105-X12	<b>4-5</b>

color fastness to dry rubbing

EN ISO 105-X12

4-5

seam slippage

EN ISO 13 936-2

**warp 5 mm**  
**weft 4 mm**

## Applications / parameters

upholstery



decorative



oekeo tex



## Maintenance



gentle wash at maximum 30 °c



bleaching with non-chlorine allowed



tolerates ironing up to 150 °c



gentle dry cleaning using hydrocarbones and tetrachloroethene



drip dry

If stained, clean topically with water and white soap, first gently dry with a cloth, then let dry naturally. Vacuum regularly. Do not wash, do not dry clean. Do not use aggressive cleaning agents.

## Before you order

1. Colour shades may vary slightly between production lots.
2. Information presented on this website does not constitute a trade offer.
3. Product technical parameters contained in the safety data sheet are based on the manufacturer's data.
4. Data on maintenance (cleaning methods) pertains to the fabrics we sell, not to finished products comprising different elements.
5. Before cutting the fabric, please verify the quantity delivered, quality of materials and conformity with the order.
6. With complete rolls of textiles, the length may differ slightly from the value declared.
7. In case of any doubts regarding the use of our products, visit the TIPS section at [www.dekoma.eu](http://www.dekoma.eu) or contact us directly.
8. Colours of products presented on this website may differ from the actual colours.
9. Due to the specific character of the production process, the parameters provided i.e. width, height, grammage, and repeat may differ slightly from the values declared.