

## PRODUCT DATA SHEET



product name:**SALO**

collection:**GARDA**

### Basic information

|                        | Result                     |
|------------------------|----------------------------|
| width total (+/-)      | <b>142 cm</b>              |
| width usable (+/-)     | <b>140 cm</b>              |
| report ↑               | <b>0.7 cm</b>              |
| report →               | <b>0.8 cm</b>              |
| weight (+/-)           | <b>585 g/m<sup>2</sup></b> |
| roll lenght (+/- 5m)   | <b>35 m</b>                |
| minimal order quantity | <b>0.1 m</b>               |
| quantity of colours    | <b>7</b>                   |

### Composition

|                 |             |
|-----------------|-------------|
| recycled cotton | <b>100%</b> |
|-----------------|-------------|

### Technical data

|                               | Norm           | Result                              |
|-------------------------------|----------------|-------------------------------------|
| abrasion resistance           | EN ISO 12 947  | <b>&gt;70 000 Martindale cycles</b> |
| colour resistance to light    | EN ISO 105-B02 | <b>4-5</b>                          |
| color fastness to wet rubbing | EN ISO 105-X12 | <b>4</b>                            |

|                               |                 |                                    |
|-------------------------------|-----------------|------------------------------------|
| color fastness to dry rubbing | EN ISO 105-X12  | <b>4-5</b>                         |
| shrinkage wet                 | ISO 675         | <b>warp 7,8%<br/>weft 7,8%</b>     |
| shrinkage dry                 |                 | <b>warp 4,5%<br/>weft 4,5%</b>     |
| seam slippage                 | EN ISO 13 936-2 | <b>warp 5,2 mm<br/>weft 3,8 mm</b> |
| pilling                       | EN ISO 12 945-2 | <b>3-4</b>                         |

## Applications / parameters

upholstery



decorative



oekeo tex



recycled



## Maintenance



wash at maximum 30 °c



do not bleach



tolerates ironing up to 110 °c



gentle dry deaning using hydrocarbones and tetrachloroethene



do not tumble dry

## Before you order

1. Colour shades may vary slightly between production lots.
2. Information presented on this website does not constitute a trade offer.
3. Product technical parameters contained in the safety data sheet are based on the manufacturer's data.
4. Data on maintenance (cleaning methods) pertains to the fabrics we sell, not to finished products comprising different elements.
5. Before cutting the fabric, please verify the quantity delivered, quality of materials and conformity with the order.
6. With complete rolls of textiles, the length may differ slightly from the value declared.
7. In case of any doubts regarding the use of our products, visit the TIPS section at [www.dekoma.eu](http://www.dekoma.eu) or contact us directly.

8. Colours of products presented on this website may differ from the actual colours.
9. Due to the specific character of the production process, the parameters provided i.e. width, height, grammage, and repeat may differ slightly from the values declared.