PRODUCT DATA SHEET

product name:**TACORA**
collection:**TACORA**

Basic information

	Result
width total (+/-)	**302 cm**
width usable (+/-)	**300 cm**
weight (+/-)	**280 g/m^2**
roll lenght (+/- 5m)	**25 m**
minimal order quantity	**0.1 m**
quantity of colours	**41**

Composition

recycled polyester fr	**51%**
polyester fr	**49%**

Technical data

	Norm	Result
abrasion resistance	EN ISO 12 947-2	**50 000 Martindale cycles**
colour resistance to light	EN ISO 105-B02	**5**
shrinkage wet	ISO 5077 / ISO 6330 / ISO 3759	**warp 0%** **weft 0%**

colour fastness to washing	EN ISO 105-C06	**5**
colour fastness to dry washing	EN ISO 105-D01	**5**
thermal resistance		**0.039779 m²K/W**
seam slippage	EN ISO 13 936-2	**warp 4,4 mm** **weft 3 mm**
pilling	EN ISO 12 945-2	**4-5**
snagging	ASTM D3939/D3939M-13	**3**

Flame retardant standards

Norm	Foam	Result
EN 13773		**Class 1**
NF P 92-507		**M1**
DIN 4102		**B1**
ISO 6940/6941		**passed**

Applications / parameters

flame retardant   curtains   decorative

oeko tex   recycled   wide

Maintenance

gentle wash at maximum 30 °c

do not bleach

tolerates ironing up to 110 °c

(P) normal dry deaning using hydrocarbones and tetrachloroethene

⊠ do not tumble dry

Before you order

1. Colour shades may vary slightly between production lots.
2. Information presented on this website does not constitute a trade offer.
3. Product technical parameters contained in the safety data sheet are based on the manufacturer's data.
4. Data on maintenance (cleaning methods) pertains to the fabrics we sell, not to finished products comprising different elements.
5. Before cutting the fabric, please verify the quantity delivered, quality of materials and conformity with the order.
6. With complete rolls of textiles, the length may differ slightly from the value declared.
7. In case of any doubts regarding the use of our products, visit the TIPS section at www.dekoma.eu or contact us directly.
8. Colours of products presented on this website may differ from the actual colours.
9. Due to the specific character of the production process, the parameters provided i.e. width, height, grammage, and repeat may differ slightly from the values declared.