PRODUCT DATA SHEET

product name:**TWILIGHT**
collection:**TWILIGHT**

Basic information

	Result
width total (+/-)	**304 cm**
width usable (+/-)	**302 cm**
weight (+/-)	**322 g/m^2**
roll lenght (+/- 5m)	**30 m**
minimal order quantity	**0.1 m**
quantity of colours	**25**

Composition

polyester	**100%**

Technical data

	Norm	Result
abrasion resistance	ISO 12 497-2	**30 000 Martindale cycles**
colour resistance to light	EN ISO 105-B02	**4**
colour fastness to wet rubbing	EN ISO 105-X12	**4-5**
color fastness to dry rubbing	EN ISO 105-X12	**4-5**

| shrinkage wet | ISO 5077 / ISO 6330 / ISO 3759 | **warp 0,36%** |
| | | **weft +0,07%** |

| shrinkage dry | ISO 3175-2 / ISO 3759 | **warp +0,17%** |
| | | **weft 0,21%** |

| seam slippage | EN ISO 13 936-2 | **warp 3 mm** |
| | | **weft 4 mm** |

| pilling | EN ISO 12 945-2 | **4** |

Flame retardant standards

Norm	Foam	Result
NFPA 701		**passed**
FMVSS 302		**passed**

Applications / parameters

curtains

dimout

decorative

oeko tex

reach

wide

Maintenance

gentle wash at maximum 30 °c

do not bleach

tolerates ironing up to 110 °c

gentle dry cleaning using hydrocarbones and tetrachloroethene

tumble drying at maximum 60 °c

Before you order

1. Colour shades may vary slightly between production lots.

2. Information presented on this website does not constitute a trade offer.
3. Product technical parameters contained in the safety data sheet are based on the manufacturer's data.
4. Data on maintenance (cleaning methods) pertains to the fabrics we sell, not to finished products comprising different elements.
5. Before cutting the fabric, please verify the quantity delivered, quality of materials and conformity with the order.
6. With complete rolls of textiles, the length may differ slightly from the value declared.
7. In case of any doubts regarding the use of our products, visit the TIPS section at www.dekoma.eu or contact us directly.
8. Colours of products presented on this website may differ from the actual colours.
9. Due to the specific character of the production process, the parameters provided i.e. width, height, grammage, and repeat may differ slightly from the values declared.